



High Performance Paint Product Data Sheet



100% ACRYLIC LOW SHEEN

OX-139X JUN 09



DESCRIPTION: High quality exterior 100% acrylic coating. Formulated with high pigmentation and quality resins to give excellent opacity and durability.

TYPICAL USES: General exterior finish for EIFS, fibrolite, plaster cladding systems and timber weatherboards.

PERFORMANCE: Gives trouble free life of 10 years or more when applied correctly on a sound substrate. Has self priming properties which in many applications eliminates the need for a primer coat.

LIMITATIONS: It is recommended that new concrete surfaces age before painting. Weathering will reduce gloss level over time. Do not apply if the air and surface temperature during application and drying is likely to fall below 10°C.

TECHNICAL DATA:

Resin:	100% acrylic
Solvent:	Water
Finish:	Low Sheen (10-15% @ 60°)
Colour:	White/Unlimited Colours
Touch Dry (minimum):	60 minutes @ 20°C
Recoat Time (minimum):	2-4 hours
Primer:	See over
Number of Coats:	2 usually required
Dry Film Thickness:	
Wet Film Thickness:	85-100 microns
Durability:	Excellent
Thinning and Clean Up:	Water
VOC:	
Pot Life:	Not Applicable
Pack Size:	1, 4, 10 Litre

SPREAD RATE:

Theoretical Coverage:	10-12 m ² /litre/coat.
Coverage depends on surface profile and porosity.	

COMPUTER CODES:

100% Acrylic L/Sheen White	01-139
100% Acrylic L/Sheen Midtone	02-1392
100% Acrylic L/Sheen Deep	02-1393
100% Acrylic L/sheen Ultra Deep	02-1394
100% Acrylic L/Sheen Accent	02-1395

Coating Technologies Limited, 16 Aetna Place, Henderson, Auckland, New Zealand

Phone: 0064 9 837 0897 Fax: 0064 9 837 3736 www.cotec.co.nz

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from the date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.

100% ACRYLIC LOW SHEEN

SURFACE PREPARATION:

(Refer to "Surface Preparation and Paint Systems" for full details). To ensure a successful application all surfaces to be coated must be clean, dry and stable.

All cracks and joints need to be treated as appropriate to suit the situation. Do not expect paint to bridge moving cracks/joints successfully.

Any mould, moss or algae needs to be treated with a suitable chemical cleaner/inhibitor. Ensure surfaces are free from oil, grease and any surface contamination. Use commercial detergent/alkali cleaner.

Note: Commencement of work on a surface means in general you accept that surface is in a suitable condition. If any doubt about condition etc, seek advice.

CONCRETE, CEMENT PLASTER:

Unpainted: Allow new cementitious surfaces to cure for a minimum of 7 days before painting (28 days is preferable). Remove any dirt, loose material and laitance by water blasting. Allow to dry. If lime leaching/efflorescence is likely, apply 1 coat of LIME STOP.

Painted: Remove any flaking or blistering paint by water blasting or grit blasting. Check surface is sound by cross-cutting with a sharp blade then applying tape. Rip tape off. If paint pulls away the surface is unsound. In this case stripping is required prior to painting.

FIBROLITE/EIFS SYSTEMS:

The surfaces need to be clean and dry. Generally no primer is required. Prepare as for concrete and cement plaster.

WOOD:

Remove any flaking or blistering paint and check soundness of surface as above. Generally a primer is required to fill and seal the surface of bare timber. On exterior work use ALKYD WOOD PRIMER or ACRYLIC SEALER UNERCOAT. On interior surfaces use EVO EASYSAND or HI OPACITY PIGMENTED SEALER. Staining can result from the sap of some timbers. Oily native timbers may show or prevent the drying of oil based primers.

APPLICATION:

ROLLER: Lambs wool (nap dependant on substrate texture)

SPRAY: Airless (2500psi minimum. 515 tip or larger)

BRUSH: Good quality brush.

THINNING & CLEAN UP:

Maximum thinning 10% water for spraying. Clean up in water. Use a small amount of detergent to aid clean up.

ENVIRONMENTAL:

The evolution (EVO) range of products are formulated on the latest available resins to give you both high performance and also to meet low VOC (Volatile Organic Compound) levels set out in current local standards. Likewise levels of environmentally harmful substances are either significantly reduced or eliminated. DO NOT POUR paint or wash down storm water or water courses. ALWAYS dispose of in accordance with local Government regulations. Soak up spills with absorbent material and dispose of properly. If spraying use suitable respiratory protection. Refer to the MATERIAL SAFETY DATA SHEET.